



IS410

Lead-free Epoxy Laminate and Prepreg

IS410 is a high-performance FR-4 epoxy laminate and prepreg system designed to support the printed circuit board industry's requirements for higher levels of reliability and the trend to use lead-free solder.

Isola's IS410 has a glass transition temperature (Tg) of 180°C and is specially formulated for superior performance through multiple thermal excursions, passing 6X solder tests at 288°C. IS410 is optimized for enhanced drilling performance allowing high aspect ratio holes of ≤ 10 mils. Its unique resin chemistry provides CAF resistance with the benefit of long-term reliability of boards built with small feature designs.

Product Attributes

Legacy Materials

Typical Market Applications

Aerospace & Defense , Consumer Electronics , Networking & Communication Systems , Medical, Industrial & Instrumentation , Automotive & Transportation

ORDERING INFORMATION:

Contact your local sales representative or visit www.isola-group.com for further information.

Isola Group
3100 West Ray Road
Suite 301
Chandler, AZ 85226
Phone: 480-893-6527
Fax: 480-893-1409
info@isola-group.com

Isola Asia Pacific (Hong Kong) Ltd.
Unit 3512 - 3522, 35/F
No. 1 Hung To Road, Kwun Tong,
Kowloon, Hong Kong
Phone: 852-2418-1318
Fax: 852-2418-1533
info.hkg@isola-group.com

Isola GmbH
Isola Strasse 2
D-52348 Düren,
Germany
Phone: 49-2421-8080
Fax: 49-2421-808164
info-dur@isola-group.com

Data Sheet

Tg 180°C

Td 350°C

Dk 3.97

Df 0.02

IPC-4101 - / 21 / 24 / 26 / 121 / 124 / 129

UL - File Number E41625

Last Updated April 5, 2018
Revision No: B

Product Features

- Industry Recognition
 - UL File Number: E41625
 - RoHS Compliant
- Performance Attributes
 - Lead-free assembly compatible
 - 6x 288°C solder float capable
- Processing Advantages

Product Availability

- Standard Material Offering: Laminate
 - 2 to 125 mil (0.05 to 3.2 mm)
 - Available in full size sheet or panel form
- Copper Foil Type
 - HTE Grade 3
 - RTF (Reverse Treat Foil)
- Copper Weight
 - ½ to 2 oz (18 to 70 μ m) available
 - Heavier copper available
 - Thinner copper foil available
- Standard Material Offering: Prepreg
 - Roll or panel form
 - Tooling of prepreg panels
- Glass Fabric Availability
 - E-glass
 - Square weave glass

Property	Typical Value	Units	Test Method
		Metric (English)	IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DSC	180	°C	2.4.25C
Decomposition Temperature (Td) by TGA @ 5% weight loss	350	°C	2.4.24.6
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	50 10	Minutes 2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	55 250 3.5	ppm/°C ppm/°C % 2.4.24C 2.4.24C
X/Y-Axis CTE	Pre-Tg	11	ppm/°C 2.4.24C
Thermal Conductivity		0.5	W/mK ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual 2.4.13.1
Dk, Permittivity	A. @ 100 MHz B. @ 1 GHz C. @ 2 GHz D. @ 5 GHz E. @ 10 GHz	3.96 3.90 3.97 3.87 3.87	— 2.5.5.3 2.5.5.9 Bereskin Stripline Bereskin Stripline Bereskin Stripline
Df, Loss Tangent	A. @ 100 MHz B. @ 1 GHz C. @ 2 GHz D. @ 5 GHz E. @ 10 GHz	0.0149 0.0189 0.0200 0.0230 0.0230	— 2.5.5.3 2.5.5.9 Bereskin Stripline Bereskin Stripline Bereskin Stripline
Volume Resistivity	A. After moisture resistance B. At elevated temperature	8.0 x 10 ⁸ 3.6 x 10 ⁸	MΩ-cm 2.5.17.1
Surface Resistivity	A. After moisture resistance B. At elevated temperature	8.0 x 10 ⁶ 4.5 x 10(8)	MΩ 2.5.17.1
Dielectric Breakdown		>50	kV
Arc Resistance		129	Seconds
Electric Strength (Laminate & laminated prepreg)		44 (1100)	kV/mm (V/mil)
Comparative Tracking Index (CTI)		3 (175-249)	Class (Volts) UL 746A ASTM D3638
Peel Strength	A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil] B. Standard profile copper 1. After thermal stress 2. At 125°C (257°F) 3. After process solutions	1.14 (6.5) 1.225 (7.0) 1.14 (6.5) 0.90 (5.1)	N/mm (lb/inch) 2.4.8C 2.4.8.2A 2.4.8.3 2.4.8.3
Flexural Strength	A. Length direction B. Cross direction	82.6 66.4	ksi 2.4.4B
Tensile Strength	A. Length direction B. Cross direction	60.9 45.8	ksi ASTM D3039
Poisson's Ratio	A. Length direction B. Cross direction	0.175 0.143	— ASTM D3039
Moisture Absorption		0.20	% 2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0	Rating UL 94
Max Operating Temperature		130	°C UL 796

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

www.isola-group.com/products/all-printed-circuit-materials/is410/

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. IS410 is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners.

© 2016, Isola Group, All rights reserved.



NOTE

Visit our site <http://www.isola-group.com> for more details.
Revision B: Corrected units for Flexural and Tensile Strength