



IS415HR High Thermal Performance Epoxy Material

IS415HR is a proprietary high-performance 180°C glass transition temperature (Tg) FR-4 system for multilayer Printed Wiring Board (PWB) applications where maximum thermal maximum thermal performance and reliability are required. This product is also ideally suited for designs requiring high signal integrity. IS415HR has a lower Z-axis CTE and provides superior moisture resistance at reflow, resulting in a product that bridges the gap from both a thermal and electrical perspective.

www.isola-group.com/products/IS415HR

ORDERING INFORMATION:

Contact your local sales representative or visit www.isola-group.com for further information.

Isola Group
3100 West Ray Road
Suite 301
Chandler, AZ 85226
Phone: 480-893-6527
Fax: 480-893-1409
info@isola-group.com

Isola Asia Pacific (Hong Kong) Ltd.
Unit 3512 - 3522, 35/F
No. 1 Hung To Road, Kwun Tong,
Kowloon, Hong Kong
Phone: 852-2418-1318
Fax: 852-2418-1533
info.hkg@isola-group.com

Isola GmbH
Isola Strasse 2
D-52348 Düren, Germany
Phone: 49-2421-8080
Fax: 49-2421-808164
info-dur@isola-group.com

High Performance

IS415HR Data Sheet

Tg 180, Td 360
Dk 3.80, Df 0.0123
/98 /99/ 101 /126

Features

- High Thermal Performance
 - ▶ High Tg: 180°C (DSC)
 - ▶ High Td: 360°C (TGA @ 5% wt loss)
 - ▶ Low CTE in the Z-axis – 2.5% (50-260°C)
- T260: 60 minutes
- T288: >30 minutes
- Lead-free Compatible and RoHS Compliant
- UV Blocking and AOI Compatible
 - ▶ High throughput and accuracy during PCB fabrication and assembly
- Superior Processing
 - ▶ Closest to conventional FR-4 processing of all high-speed materials
- Core Material Standard Availability
 - ▶ Thickness: 0.002 (0.05 mm) to 0.028 (0.71 mm)
 - ▶ Available in full size sheet or panel form
- Prepreg Standard Availability
 - ▶ Roll or panel form
 - ▶ Tooling of prepreg panels available
- Copper Foil Type Availability
 - ▶ Standard HTE Grade 3
 - ▶ RTF (Reverse Treat Foil)
- Copper Weights
 - ▶ ½, 1 and 2 oz (18, 35 and 70 µm) available
 - ▶ Heavier copper available upon request
 - ▶ Thinner copper foil available upon request
- Glass Fabric Availability
 - ▶ Standard E-glass
 - ▶ Square weave glass fabric available
 - ▶ Spread glass fabric available
- Industry Approvals
 - ▶ IPC-4101D WAM1 /98 /99/ 101 /126 (IPC-4101C /21 /24 /26 /121 /124 /129)
 - ▶ UL - File Number E41625
 - ▶ Qualified to UL's MCIL Program

IS415HR Typical Values

Property	Typical Values			
		Units	Test Method	
	Typical Value	Metric (English)	IPC-TM-650 (or as noted)	
Glass Transition Temperature (Tg) by DSC	180	°C	2.4.25	
Decomposition Temperature (Td) by TGA @ 5% weight loss	360	°C	ASTM D3850	
T260	60	Minutes	ASTM D3850	
T288	>30	Minutes	ASTM D3850	
CTE, Z-axis	A. Pre-Tg B. Post-Tg	38 220	ppm/°C	2.4.24
CTE, X-, Y-axes	A. Pre-Tg B. Post-Tg	13 14	ppm/°C	2.4.24
Z-axis Expansion (50-260°C)		2.5	%	2.4.24
Thermal Conductivity		0.4	W/mK	ASTM D5930
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Rating	2.4.13.1
Dk, Permittivity (Laminate & prepreg as laminated) Tested at 56% resin	A. @ 1 GHz (HP4291A) B. @ 2 GHz (Bereskin Stripline) C. @ 5 GHz (Bereskin Stripline) D. @ 10 GHz (Bereskin Stripline)	3.85 3.80 3.79 3.77	–	2.5.5.9 2.5.5.5 2.5.5.5 2.5.5.5
Df, Loss Tangent (Laminate & prepreg as laminated) Tested at 56% resin	A. @ 1 GHz (HP4291A) B. @ 2 GHz (Bereskin Stripline) C. @ 5 GHz (Bereskin Stripline) D. @ 10 GHz (Bereskin Stripline)	0.0121 0.0123 0.0122 0.0125	–	2.5.5.9 2.5.5.5 2.5.5.5 2.5.5.5
Volume Resistivity	A. 96/35/90 B. After moisture resistance C. At elevated temperature	– 4.70x10 ⁷ 9.80x10 ⁷	MΩ-cm	2.5.17.1
Surface Resistivity	A. 96/35/90 B. After moisture resistance C. At elevated temperature	– 2.70x10 ⁸ 2.40x10 ⁶	MΩ	2.5.17.1
Dielectric Breakdown		>60	kV	2.5.6
Arc Resistance		120	Seconds	2.5.1
Electric Strength (Laminate & prepreg as laminated)		40 (1100)	kV/mm (V/mil)	2.5.6.2
Comparative Tracking Index (CTI)		3 (175-249)	Class (Volts)	UL-746A ASTM D3638
Peel Strength	A. Standard profile copper 1. After thermal stress 2. At 125°C (257°F) 3. After process solutions	0.82 (4.6) 0.77 (4.3) 0.64 (3.6)	N/mm (lb/inch)	2.4.8.2 2.4.8.3 –
Flexural Strength	A. Lengthwise direction B. Crosswise direction	74,200 51,600	lb/inch ²	2.4.4
Tensile Strength	A. Lengthwise direction B. Crosswise direction	43,750 31,520	lb/inch ²	–
Young's Modulus	A. Grain direction B. Fill direction	3530 3200	ksi	ww
Poisson's Ratio	A. Grain direction B. Fill direction	0.158 0.138	–	xx
Moisture Absorption		0.15	%	2.6.2.1
Flammability (Laminate & prepreg as laminated)		V-0	Rating	UL 94
Max Operating Temperature		130	°C	–

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

www.isola-group.com/products/IS415HR



The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. All other trademarks mentioned herein are property of their respective owners. © 2016, Isola Group, All rights reserved.